



SELECTION & SPECIFICATION DATA

Type	Cold Adhesive
Description	Blackhawk 5360 Roofing Adhesive is our high performance cold adhesive. It is a single component, asbestos-free, asphaltic commercial roofing adhesive used to adhere modified bitumen roofing membranes.
Features	<ul style="list-style-type: none"> • Single-component • Low odor • Cold-applied • Elastomeric
Uses	Adhesive for single- and multi-ply SBS and select APP roofing membranes.
Color	Black
Primer	Self-priming
Solids Content	78% by weight
VOC Value(s)	<250 g/L (2.09 lbs/gal)
Limitations	Not all APP membranes are alike, and adhesion to these modified membranes should be tested. Do not use with membranes containing a burn-off film.

SUBSTRATES & SURFACE PREPARATION

All	All surfaces must be clean and free from debris and loose scale material or anything that may interfere with adhesion or act as a bond breaker with the desired substrate.
------------	--

SAFETY

Safety	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.
---------------	--

Ventilation	Use in well ventilated areas
--------------------	------------------------------

MIXING & THINNING

Mixing	No mixing necessary
Thinning	Do not thin
Cleanup	Mineral spirits or similar solvent

PACKAGING, ESTIMATING & HANDLING

ITEM #	PACKAGING
K-5360-005-001	Pail - 4.7 gallons
Theoretical Coverage Rate	1.5 – 2 gallons per 100 square feet, depending on substrate
Storage & Shelf Life	Estimated shelf life is 12 months when stored in a dry area at 75°F (24°C). When kept at recommended storage conditions and in original unopened containers. Actual shelf life may vary with storage conditions. Do not store below 40°F (4°C) or above 110°F (43°C). Store indoors. Always inspect the product prior to use.

TYPICAL PHYSICAL PROPERTIES

Lap shear testing after 24 hours has shown that Blackhawk 5360 Roofing Adhesive meets or exceeds the performance attributes of ASTM D3019.

Rev 12/21

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.